

# OAK SANJO

Top layer approx. 2,5 mm

Maintenance oil



placid

### No initial oil treatment is required!

Further information about our products can be found in our Ondo maintenance and installation instructions or at [admonter.at](http://admonter.at).



### Ondo FLOORs on underfloor heating systems

Ondo FLOORs are ideally suited for underfloor heating systems. We suggest that our products ideally are fully glued down for best results with Admonter elastic adhesive. However, like all engineered boards our planks can be laid as a floating installation. We recommend hot-water underfloor heating systems set at low temperature. Please find detailed information in the information sheet Ondo FLOORs on underfloor heating systems!

### Admonter accessories

The wide range of accessories matches the Ondo FLOORs and includes flush-mount skirting and solutions for staircases.

### Regular care and maintenance

Please see the Ondo maintenance & installation instructions or visit [www.ondo-naturholzboden.at](http://www.ondo-naturholzboden.at).

| Grading | Thickness (mm) | Construction | Width (mm) |         | Length (mm)        | Texture | Finish | Profile                   |
|---------|----------------|--------------|------------|---------|--------------------|---------|--------|---------------------------|
| placid  | 13             | 3-layer      | 158        | classic | 1850 / 2000 / 2400 | brushed | ec     | lock-it / Tongue & groove |
|         |                |              | 192        | classic | 1850 / 2000 / 2400 | brushed | ec     | lock-it / Tongue & groove |
| vivid   | 13             | 3-layer      | 158        | classic | 1850 / 2000 / 2400 | brushed | ec     | lock-it / Tongue & groove |
|         |                |              | 192        | classic | 1850 / 2000 / 2400 | brushed | ec     | lock-it / Tongue & groove |

Backing: Solid Wood / ec: natural oiled easy care

### Technical information

More information (for example concerning fire classification) in the accompanying information to CE-marking at <http://www.admonter.eu/en/downloads/>

| Type of wood | Thickness (mm) | Weight [kg/m <sup>2</sup> ] | Moisture content [%] | Lambda [W/m K] | d-Value R [m <sup>2</sup> K/W] | Hardness [N/mm <sup>2</sup> ] | Fire classification |
|--------------|----------------|-----------------------------|----------------------|----------------|--------------------------------|-------------------------------|---------------------|
| Oak          | 13             | 6,7                         | 7+/-2                | 0,13           | 0,098                          | 41                            | C <sub>s</sub> -s1  |

